

FIRE TECHNOLOGY SERVICES

Confidential Report

Our Ref: 27/03316M/10/14

Notified Body for PPE Directive, Construction Products Regulation & Marine Equipment Directive I.D. No. 0338 & 0339

Fire Technology Services
A division of BTTG T & C Ltd
Wira House, West Park Ring Road,
Leeds, LS16 6QL





Tel No: +44 (0)113 25919969 Fax No: +44 (0)113 2780306



Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

Page 1 of 5

17 October 2014

Our Ref: 27/03316M/10/14

Your Ref:

Client: Gudbrandsdalens Uldvarefabrik

Serviceboks

N-2626 Lillehammer

Norway

Job Title: Fire Test on One Sample of Fabric

Clients Order Ref: ---

Date of Receipt: 9 October 2014

Description of Sample: One sample of fabric, referenced: **5055 Vadal**.

Work Requested: Fire Technology Services were requested to carry out a fire test on

the sample supplied to IMO FTP Code 2010:Part 8.







> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014 Page 2 of 5

Our Ref: 27/03316M/10/14

Your Ref:

Gudbrandsdalens Uldvarefabrik

Product Description Sheet

Company Name	Gudbrandsdalens Uldvarefabrik AS			
FABRIC				
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Seats, sofas and office chairs			
Name and/or Identification of the Product Tested	5055 Vadal			
Materials of the Product and its Composite Ratio (i)	87% wool / 5% viscose / 8% polyamide			
Composition of Weave (ii)	Modified twill			
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	cm: 11,6 / 9,2			
Yarn Number Count	Nm 5,7			
Thickness (mm)				
Mass per Unit Area (g/mm²)	500 g/m²			
Colour and Tone (iii)	Colour range of 22 piece dyed melange colours			
Method and Quantity of Fire Retardant Treatment	No treatment			

- Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.







Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014 Page 3 of 5

Our Ref: 27/03316M/10/14

Your Ref:

Gudbrandsdalens Uldvarefabrik

FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 8 (replacing IMO A652 (16)) Test for Upholstered Furniture

Date of Test: 16/10/2014

Conditioning

Immediately prior to testing the sample was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 20 $\pm 5^{\circ}$ C temperature and 50 \pm 20% relative humidity for at least 16 hours.

The sample was tested in a room of volume 25m³ and 16°C.

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of standard non-FR polyurethane foam of density about 22Kg/m³.

Requirements

<u>Ignition Source 0</u> No progressive smouldering or flaming within one hour of the placement

of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120sec of

removal of the burner tube.







Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014 Page 4 of 5

Our Ref: 27/03316M/10/14

Your Ref:

Gudbrandsdalens Uldvarefabrik

Results

Ignition Source	Specimen 1		Specimen 2	
	0	1	0	1
Ignition Time (secs.)		16		DNP
Extinction Time (Flame) (secs.)		20		20
Extinction Time (Smoke) (secs.)	2509	24	DNP	25
Time of Cover Split (secs.)	DNS	DNS	DNS	DNS

Observations				
Cigarette Did Not Propagate			\boxtimes	
Manually Extinguished				
Burnt Through Thickness of Foam				
Material Did Not Split	\boxtimes	\boxtimes	\boxtimes	\boxtimes
Burnt to Edge of Specimen				
Escalating Combustion				
Escalating Smouldering				
Did Not Observe Time of Event				

Cigarette Specification (Source 0)

Dimensions (mm) 69 Mass (g) 0.90 Smouldering Rate (secs) 650

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.







Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014 Page 5 of 5

Our Ref: 27/03316M/10/14

Your Ref:

Gudbrandsdalens Uldvarefabrik

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 8.

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Enquiries concerning this report should be addressed to Customer Services.



