

FIRE TECHNOLOGY SERVICES

Confidential Report

Our Ref: 27/03316K/10/14

Notified Body for PPE Directive, Construction Products Regulation & Marine Equipment Directive I.D. No. 0338 & 0339 Fire Technology Services A division of BTTG T & C Ltd Wira House, West Park Ring Road, Leeds, LS16 6QL



Tel No: +44 (0)113 25919969 Fax No: +44 (0)113 2780306



> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014		
Our Ref: 27/03316K/10/14 Your Ref:		Page 1 of 5
Client:	Gudbrandsdalens Uldvarefabrik Serviceboks N-2626 Lillehammer Norway	
Job Title:	Fire Test on One Sample of Fabric	
Clients Order Ref:		
Date of Receipt:	9 October 2014	
Description of Sample:	One sample of fabric, referenced: 5516 Modal Point.	
Work Requested:	Fire Technology Services were requested to carry out the sample supplied to IMO FTP Code 2010:Part 8.	a fire test on





> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014

Page 2 of 5

Our Ref: 27/03316K/10/14 Your Ref:

Gudbrandsdalens Uldvarefabrik

Product Description Sheet

Company Name	Gudbrandsdalens Uldvarefabrik AS		
FABRIC			
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Seats, sofas and office chairs		
Name and/or Identification of the Product Tested	5515 Modal / 5516 Modal Point / 5517 Modal Moulinex		
Materials of the Product and its Composite Ratio (i)	70% wool / 30% viscose		
Composition of Weave (ii)	Plain weave		
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	cm: 5,6 / 5,4		
Yarn Number Count	Nm 4,5/2		
Thickness (mm)			
Mass per Unit Area (g/mm²)	535 g/m²		
Colour and Tone (iii)	Colour range of 50 colours		
Method and Quantity of Fire Retardant Treatment	No treatment		

(i) Such as wool, nylon, polyester, etc.

(ii) Such as plain, weave, twilled.

(iii) If the product has a pattern, the representative colour shall be described.





> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014

Page 3 of 5

Our Ref: 27/03316K/10/14 Your Ref:

Gudbrandsdalens Uldvarefabrik

FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 8 (replacing IMO A652 (16)) Test for Upholstered Furniture

Date of Test: 16/10/2014

Conditioning

Immediately prior to testing the sample was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 20 \pm 5°C temperature and 50 \pm 20% relative humidity for at least 16 hours.

The sample was tested in a room of volume 25m³ and 19°C.

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of standard non-FR polyurethane foam of density about 22Kg/m³.

Requirements

Ignition Source 0 No progressive smouldering or flaming within one hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120sec of removal of the burner tube.





> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014

Page 4 of 5

Our Ref: 27/03316K/10/14 Your Ref:

Gudbrandsdalens Uldvarefabrik

Results

	Specimen 1		Specimen 2	
Ignition Source	0	1	0	1
Ignition Time (secs.)		10		14
Extinction Time (Flame) (secs.)		20		21
Extinction Time (Smoke) (secs.)	2241	25	2200	25
Time of Cover Split (secs.)	DNO	DNS	DNO	DNS
Observations				
Cigarette Did Not Propagate Manually Extinguished Burnt Through Thickness of Foam Material Did Not Split Burnt to Edge of Specimen Escalating Combustion Escalating Smouldering Did Not Observe Time of Event				

Cigarette Specification (Source 0)

Dimensions (mm)	69
Mass (g)	0.90
Smouldering Rate (secs)	650

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.





> Tel: +44 (0)113 259 1999 Fax: +44 (0)113 278 0306 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

17 October 2014

Page 5 of 5

Our Ref: 27/03316K/10/14 Your Ref:

Gudbrandsdalens Uldvarefabrik

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 8.

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

..... P Doherty, Operational Head Reported by:....

Enquiries concerning this report should be addressed to Customer Services.

