



TESTING • CERTIFICATION • AUDITING

Confidential Report

Our Ref: 54221-1-1



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 9 November 2017

Our Ref: 54221-1-1
Your Ref: -

Page: 1 of 5

Client: Gudbrandsdalens Uldvarefabrik AS
Mortrudveien 3-5
NO-2609 Lillehammer
Norway

Job Title: Fire Test on One Sample of Fabric

Client's Order No: -

Date of Receipt: 23 October 2017

Description of Sample(s): One sample identified as follows was received for testing:
5215 Heddal Stitched

Work Requested: We were asked to make the following test(s):
IMO FTP Code 2010 Part 8 (Upholstered Furniture)

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 9 November 2017

Our Ref: 54221-1-1
Your Ref: -


Page: 2 of 5



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: info@bttg.co.uk
 Website: www.bttg.co.uk

Date: 9 November 2017

Our Ref: 54221-1-1
 Your ref: -

Page: 3 of 5

Client: Gudbrandsdalens Uldvarefabrik AS

Product Description Sheet

Company Name	Gudbrandsdalens Uldvarefabrik AS
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc.;	Seats, sofas and office chairs
Name and/or Identification of the Product Tested	5215 Heddal Stitched
Materials of the Product and its Composite Ratio (i)	90% Wool / 10% Polyamide
Composition of Weave (ii)	Dobby Basket Weave
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Cm: 14,6 / 8,3
Yarn Number Count	Nm 18 / Nm 3
Thickness (mm)	2,1
Mass per Unit Area (g/mm ²)	880 g/m ²
Colour and Tone (iii)	Colour range of several colours
Method and Quantity of Fire Retardant Treatment	No treatment

- (i) Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
 A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
 The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
 Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 9 November 2017

Our Ref: 54221-1-1
Your ref: -

Page: 4 of 5

Client: Gudbrandsdalens Uldvarefabrik AS

FIRE TESTS ACCORDING to IMO FTP Code 2010 : Part 8 Test for Upholstered Furniture

Date of test: 31 October 2017

Conditioning

Immediately prior to testing the sample was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $20 \pm 5^{\circ}\text{C}$ temperature and $50 \pm 20\%$ relative humidity for at least 16 hours.

The sample was tested in a room of volume 25m^3 and 19°C .

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of standard non-FR polyurethane foam of density about $22\text{Kg}/\text{m}^3$.

Requirements

No progressive smouldering or flaming within one hour of the placement of the cigarette.


All progressive smouldering and flaming to cease within 120sec of removal of the burner tube.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 9 November 2017

Our Ref: 54221-1-1
Your ref: -

Page: 5 of 5

Client: Gudbrandsdalens Uldvarefabrik AS

Results

Ignition Source	Specimen 1		Specimen 2	
	0	1	0	1
Ignition Time (secs.)	-	2	-	2
Extinction Time (Flame) (secs.)	-	1	-	1
Extinction Time (Smoke) (secs.)	27	-	25	-
Time of Cover Split (secs.)	DNS	DNS	DNS	DNS
Progressive smouldering/flaming observed	No	No	No	No
Performance	PASS	PASS	PASS	PASS

DNP – Did not propagate
ME – Manually extinguished
DNS – Material did not split
BES - Burnt to edge of specimen

EC – Escalating combustion
ES – Escalating smouldering
DNO – Did not observe time of event
BTTF – Burnt through thickness of foam

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 8.

Reported by:.....
J Coleman
Fire Technician

Countersigned By:.....
P Doherty
Operational Head

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Client: Gudbrandsdalens Uldvarefabrik AS

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 9 November 2017

Our Ref: 54221-1-1
Your ref: -

Page: 6 of 5

Uncertainty Budget - Annex

The overall uncertainty budget IMO FTP Code 2010:Part 8 is as follows:-

Measurements: $\pm 1\text{mm}$
Timings: ± 2 seconds



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.