



TESTING • CERTIFICATION • AUDITING

Confidential Report

Our Ref: 53387-1-2 Supp



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 22 November 2019

Our Ref: 53387-1-2 Supp
Your Ref: -

Page: 1 of 5

Client: Gudbrandsdalen Uldvarefabrika AS
Mortrudveien 3-5
NO-2609 Lillehammer
Norway

Job Title: Fire Test on One Sample of Fabric

Client's Order No: -

Date of Receipt: 21 April 2017

Description of Sample(s): 8910 Nairobi Maxi

Work Requested: We were asked to make the following test(s):
IMO FTP Code 2010 Part 8 (Upholstered Furniture)

This is a supplementary report to the one issued on the 2nd May 2017 under our report reference 53387-1-2.

This report relates only to the samples submitted and as described in the report.

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 22 November 2019

Our Ref: 53387-1-2 Supp

Your ref: -

Page: 2 of 5

Client: Gudbrandsdalens Uldvarefabrik AS

Product Description Sheet

Company Name	Gudbrandsdalens Uldvarefabrick AS
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc.;	Seats, sofs and office chairs
Name and/or Identification of the Product Tested	8910 Nairobi Maxi
Materials of the Product and its Composite Ratio (i)	96% new wool, 4% PA
Composition of Weave (ii)	Double 5-shaft satin
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Weft: 240 picks/10cm Warp: 192 ends/10cm
Yarn Number Count	Weft: Nm 14/2, Warp: Nm 36/2
Thickness (mm)	--
Mass per Unit Area (g/m ²)	530 g/m ² , 140cm wide
Colour and Tone (iii)	Colour range: 5
Method and Quantity of Fire Retardant Treatment	No treatment

- (i) Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 22 November 2019

Our Ref: 53387-1-2 Supp
Your ref: -

Page: 3 of 5

Client: Gudbrandsdalens Uldvarefabrik AS

**FIRE TESTS ACCORDING to IMO FTP Code 2010 : Part 8
Test for Upholstered Furniture**

Date of test: 25/4/2017

Conditioning

Immediately prior to testing the sample was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $20 \pm 5^{\circ}\text{C}$ temperature and $50 \pm 20\%$ relative humidity for at least 16 hours.

The sample was tested in a room of volume 25m^3 and 17°C .

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimens were mounted over fillings of standard non-FR polyurethane foam of density about $22\text{Kg}/\text{m}^3$.

Requirements

No progressive smouldering or flaming within one hour of the placement of the cigarette.

All progressive smouldering and flaming to cease within 120sec of removal of the burner tube.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 22 November 2019

Our Ref: 53387-1-2 Supp
Your ref: -

Page: 4 of 5

Client: Gudbrandsdalens Uldvarefabrik AS

Results

Ignition Source	Specimen 1		Specimen 2	
	0	1	0	1
Ignition Time (secs.)	-	4	-	4
Extinction Time (Flame) (secs.)	-	1	-	1
Extinction Time (Smoke) (secs.)	29	-	26	-
Time of Cover Split (secs.)	DNS	DNS	DNS	DNS
Progressive smouldering/flaming observed	No	No	No	No
Performance	PASS	PASS	PASS	PASS

DNP – Did not propagate
ME – Manually extinguished
DNS – Material did not split
BES - Burnt to edge of specimen

EC – Escalating combustion
ES – Escalating smouldering
DNO – Did not observe time of event
BTTF – Burnt through thickness of foam

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 8.

Reported by:.....
J Coleman
Fire Technician

Countersigned By:.....
P Doherty
Operational Head

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Client: Gudbrandsdalens Uldvarefabrik AS

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 22 November 2019

Our Ref: 53387-1-2 Supp
Your ref: -

Page: 5 of 5

Uncertainty Budget - Annex

The overall uncertainty budget IMO FTP Code 2010:Part 8 is as follows:-

Measurements: $\pm 1\text{mm}$
Timings: ± 2 seconds



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.