



Confidential Report

Our Ref: 23/59329A/01/22





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 7 February 2022

Our Ref: 23/59329A/01/22
Your Ref: ---

Page: 1 of 5

Client: **Gudbrandsdalens Ulvarefabrik AS**

P.O Box 836
No-2626 Lillehammer
Norway

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 25 January 2022

Date Test Started: 07 February 2022

Description of Sample: One sample of fabric, which was referenced by the client as;
5218 Odal

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Date: 7 February 2022

Our Ref: 23/59329A/01/22
Your Ref: ---

Page: 2 of 5

Client: **Gudbrandsdalens Ulvarefabrik AS**

Product Description

Company Name	Gudbrandsdalens Uldvarefabrik AS
FABRIC	
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc.;	Seats, sofas and office chairs
Name and/or Identification of the Product Tested	5218 Odal
Materials of the Product and its Composite Ratio (i)	90% WO/10% PA
Composition of Weave (ii)	Twill weave
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Weft: 35,33 threads/inch Warp: 37,7 threads/inch
Yarn Number Count	Weft: Nm 3,09 Warp: Nm 36/2
Thickness (mm)	2,2 mm
Mass per Unit Area (g/m ²)	613 g/m²
Colour and Tone (iii)	Colour 222 (khaki)
Method and Quantity of Fire Retardant Treatment	none
FILLINGS	
Material (Name of Manufacturer, Type Designation)	
Type of Filling Material (eg. Foam, Polyester Fibre etc.)	
Weight per Unit Volume (kg/m ³)	
Method and Quantity of Fire Retardant Treatment	

- (i) Such as wool, nylon, polyester, etc.
(ii) Such as plain, weave, twilled.
(iii) If the product has a pattern, the representative colour shall be described.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 7 February 2022

Our Ref: 23/59329A/01/22
Your Ref: ---

Page: 3 of 5

Client: **Gudbrandsdalens Ulvarefabrik AS**

Testing to IMO FTP Code 2010 : Part 8 Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $23\pm 2^{\circ}\text{C}$ temperature and $50\pm 5\%$ relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m^3 and 17°C .

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately $20\text{-}22\text{kg/m}^3$.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm)	68mm x 8.0mm
Mass (g)	0.92
Smouldering Rate (mins/secs)	10m 59s



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: info@bttg.co.uk
 : www.bttg.co.uk

Date: 7 February 2022
 Our Ref: 23/59329A/01/22
 Your Ref: ---
 Page: 4 of 5

Client: Gudbrandsdalens Ulvarefabrik AS

Results

Cigarette Test – Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations		
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	5	5
Extinction time of flames after removal of burner (s)	1	1
Time to Cover Split (s)	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:		
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate
 ES – Escalating smouldering
 BTE – Burnt to extremities

EC – Escalating combustion
 DNS – Material did not split

ME – Manually extinguished
 DNO – Did not observe time of event





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 7 February 2022

Our Ref: 23/59329A/01/22

Your Ref: ---

Page: 5 of 5

Client: Gudbrandsdalens Ulvarefabrik AS

Comment


In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (<http://www.bttg.co.uk/decision-rules-policy>) for further information.

Uncertainty Budget

Measurements: $\pm 2\text{mm}$
Timings: ± 2 seconds.

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.